

Ish Uzina 12, Metalurgji  
 Elbasan, Albania  
 Cel: +355 682071277

# FRUTIBEST

(Plastic Pipe Factory)

## Pressure Test Report


E-mail: frutibest@yahoo.com

Test Number: t00018	Standard: GB/T 6111-2018
From ID: -	From: FRUTIBEST
Produce: -	Specimen Name: -
Material Type: -	Batch number: -
Sample No.: -	Preparation: -
Environment Temp.: -	Seal type: -
Delivery Date: 2021-02-08	Test Date: 2021-02-08
Equipment No.: -	Model: -
Checker: -	SKU Code: -
Remark: -	

Test type: Burst test	Test pressure: 80.00 Bar	
Temp.: 0.00 Bar/min	Pretreatment time: 0000:00	

	Length	Outer Dia	Thickness	Ring Stress	Station
-1	1000.00 mm	110.00 mm	6.80 mm	80.00 Bar	1

	Burst Pressure	Burst Time	Damage types
-1	34.15 Bar	00000:03:26	Break



Operator:

Checked by: