

FRUTIBEST
 (Plastic Pipe Factory)
Pressure Test Report


E-mail: frutibest@yahoo.com

| | |
|-----------------------------|--------------------------|
| Test Number: T00010 | Standard: GB/T 6111-2018 |
| From ID: - | From: Frutibest |
| Produce: TUB D110 | Specimen Name: - |
| Material Type: -HDPE 100 RC | Batch number: - |
| Sample No.: - | Preparation: - |
| Environment Temp.: - | Seal type: - |
| Delivery Date: 2021-02-08 | Test Date: 2021-02-08 |
| Equipment No.: - | Model: - |
| Checker: - | SKU Code: - |
| Remark: - | |

| | |
|-----------------------------|----------------------------|
| Test type: Hydrostatic test | Test pressure: 16.80 Bar |
| Temp.: 0.00 Bar/min | Pretreatment time: 0000:00 |
| Set time: 00070:00 | |

| | Length | Outer Dia | Thickness | Ring Stress | Station |
|----|------------|-----------|-----------|-------------|---------|
| -1 | 1000.00 mm | 110.00 mm | 6.80 mm | 16.80 Bar | 1 |

| | Start date | End date | Test time | Damage types |
|----|------------|------------|-------------|--------------|
| -1 | 2021-02-05 | 2021-02-08 | 00070:00:00 | Finish |



Operator:

Checked by: