



# ringstiffness report


## Test Report

Operator	FRUTIBEST COMPANY	Mat. Name	HDPE
Mat. Type	PLASTIC PIPE	Make Date	2024-01-09
Test For	CORRUGATED PIPE OD250 SN8	Temp	0 °C
Humi	0 %	Speed	50 mm/min
Nomin Dia	0 mm		

comment:

Num	Length mm	Int. Dia mm	Lmax mm	F@L3 N	Sp kN/m <sup>2</sup>
1	300	218.00	8.7	1053.4860	10.39

Avg	300	218.00	8.7	1053.4860	10.39
CV %	0.0	0.0	0.0	0.0	0.0



assessor: \_\_\_\_\_

ratifier: \_\_\_\_\_

test person: \_\_\_\_\_

Printed in 01-09-2024





# ringstiffness report


## Test Report

Operator	FRUTIBEST	Mat. Name	HDPE
Mat. Type	PLASTIC PIPE	Make Date	2024-01-09
Test For	CORRUGATED PIPE OD630 SN8	Temp	0 °C
Humi	0 %	Speed	50 mm/min
Nomin Dia	0 mm		

comment:

Num	Length mm	Int. Dia mm	Lmax mm	F@L3 N	Sp kN/m <sup>2</sup>
1	300	540.00	21.6	2812.4870	11.20

Avg	300	540.00	21.6	2812.4870	11.20
CV %	0.0	0.0	0.0	0.0	0.0



assessor: \_\_\_\_\_

ratifier: \_\_\_\_\_

test person: \_\_\_\_\_

Printed in 01-09-2024





# ringstiffness report


## Test Report

Operator	FRUTIBEST COMPANY	Mat. Name	HDPE
Mat. Type	PLASTIC PIPE	Make Date	2024-01-09
Test For	CORRUGATED PIPE OD500 SN8	Temp	0 °C
Humi	0 %	Speed	50 mm/min
Nomin Dia	0 mm		

comment:

Num	Length mm	Int. Dia mm	Lmax mm	F@L3 N	Sp kN/m <sup>2</sup>
1	300	432.00	17.3	2012.8920	10.02

Avg	300	432.00	17.3	2012.8920	10.02
CV %	0.0	0.0	0.0	0.0	0.0




assessor: \_\_\_\_\_

ratifier: \_\_\_\_\_

test person: \_\_\_\_\_

Printed in 01-09-2024





# ringstiffness report


## Test Report

Operator	FRUTIBEST COMPANY	Mat. Name	HDPE
Mat. Type	PLASTIC PIPE	Make Date	2024-01-09
Test For	CORRUGATED PIPE OD400 SN8	Temp	0 °C
Humi	0 %	Speed	50 mm/min
Nomin Dia	0 mm		

comment:

Num	Length mm	Int. Dia mm	Lmax mm	F@L3 N	Sp kN/m <sup>2</sup>
1	300	344.00	13.8	1572.6640	9.83

Avg	300	344.00	13.8	1572.6640	9.83
CV %	0.0	0.0	0.0	0.0	0.0




assessor: \_\_\_\_\_

ratifier: \_\_\_\_\_

test person: \_\_\_\_\_

Printed in 01-09-2024





# ringstiffness report


## Test Report

Operator	FRUTIBEST COMPANY	Mat. Name	HDPE
Mat. Type	PLASTIC PIPE	Make Date	2024-01-09
Test For	CORRUGATED PIPE OD315 SN8	Temp	0 °C
Humi	0 %	Speed	50 mm/min
Nomin Dia	0 mm		

comment:

Num	Length mm	Int. Dia mm	Lmax mm	F@L3 kN	Sp kN/m <sup>2</sup>
1	300	272.00	10.9	1.3765160	10.88

Avg	300	272.00	10.9	1.3765160	10.88
CV %	0.0	0.0	0.0	0.0	0.0



assessor: \_\_\_\_\_

ratifier: \_\_\_\_\_

test person: \_\_\_\_\_

Printed in 01-09-2024





# ringstiffness report


## Test Report

Operator	FRUTIBEST COMPANY	Mat. Name	HDPE
Mat. Type	PLASTIC PIPE	Make Date	2024-01-09
Test For	CORRUGATED PIPE OD200 SN8	Temp	0 °C
Humi	0 %	Speed	50 mm/min
Nomin Dia	0 mm		

comment:

Num	Length mm	Int. Dia mm	Lmax mm	F@L3 kN	Sp kN/m <sup>2</sup>
1	300.0000	176.00	7.0	0.7809071	9.54

Avg	300.0000	176.00	7.0	0.7809071	9.54
CV %	0.0	0.0	0.0	0.0	0.0



assessor: \_\_\_\_\_

ratifier: \_\_\_\_\_

test person: \_\_\_\_\_

Printed in 01-09-2024

